



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08K 3/00, 5/00, C08L 33/06, 51/00	A1	(11) International Publication Number: WO 99/47595 (43) International Publication Date: 23 September 1999 (23.09.99)
(21) International Application Number: PCT/GB99/00686 (22) International Filing Date: 16 March 1999 (16.03.99) (30) Priority Data: 9805487.7 17 March 1998 (17.03.98) GB (71) Applicant (for all designated States except US): IMPERIAL CHEMICAL INDUSTRIES PLC [GB/GB]; Imperial Chem- ical House, Millbank, London SW1P 3JF (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): BEVERLY, Gordon, Maxwell [GB/GB]; 38 The Coppice, Blackburn, Lancashire BB2 7BQ (GB). ELLACOTT, Michael, John [GB/GB]; Vicarage Barn, Fell Road, Waddington, Clitheroe, Lan- cashire BB7 3JQ (GB). (74) Agents: GIBSON, Sara, Hillary, Margaret et al.; ICI Group Intellectual Property, Wilton, Middlesbrough, P.O. Box 90, Cleveland TS90 8JE (GB).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: BIOCIDAL PLASTIC MATERIAL (57) Abstract <p>A plastics material comprises an acrylic polymer containing 5 – 50 % of a rubbery copolymer and a biocidal compound. The plastic material is useful as a component of a refrigerator, worktop etc. or as a building material. The material may be used as a coating for a substrate. Method of manufacturing laminate materials comprising the plastics material are also claimed.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

BIOCIDAL PLASTIC MATERIAL

The present invention relates to plastics materials, in particular to plastics which are resistant to the growth of certain microbiological species, such as fungi or bacteria.

Plastics materials are very commonly used in the manufacture of a wide variety of articles
5 such as refrigerators, worktops, shelves etc. These articles may be likely to come into contact with biological species which are harmful to health and which may spread and grow upon the surface of the article. The control of harmful microbes is also desirable in certain medical applications when the growth of bacteria etc. on benchtops, trays etc. is to be prevented. The incorporation of a biocidal compound into the plastics used in such
10 applications may therefore provide beneficial effects in that the growth of bacteria or fungi on the lining of a fridge, for example, may be inhibited.

Certain polymeric materials, e.g. polyvinylchloride, are susceptible to biological attack, especially from fungi. In order to reduce or prevent the degradation of plastics resulting from such biological attack, biocidal products have been developed for incorporation into
15 plastics materials or paints to kill the fungi or bacteria responsible or prevent their proliferation. It is also known to incorporate biocidal compounds into plastics to prevent the growth of bacteria or fungi found in food products. Examples of the latter type of product are described in US-A-5433424, JP-A-06287403 and JP-A-07071869 amongst others, and articles such as food-preparation surfaces and household food containers etc
20 are already widely available to consumers.

WO-96/29361 describes a biocidal polymeric matrix comprising a support matrix, an antimicrobial agent and a carrying agent, wherein the carrying agent and the antimicrobial agent are adapted to form at least one hydrogen bond or salt bridge therebetween.

WO 96/35205 describes a white cover for piano keys formed by injection moulding a
25 homogeneous dispersion of a methyl methacrylate resin and 0.5 - 2% of an antibacterial agent comprising a ceramic body prepared by sintering and mixing calcium phosphate and metallic silver.

WO 98/21253 describes polymers which have antimicrobial properties consisting of copolymers of non-functional vinyl monomers with vinyl comonomers of specified composition having ionic functionality.

WO 96/22023 describes the use of 2-alkyl or 2-aralkyl benzisothiazolin-3-one derivatives
5 as fungicides for plastics materials.

JP-A-08257493 describes the use of a steel plate which has a paint coating incorporating inorganic aggregates containing anti-bacterial compound, as a lining for refrigerators, freezers or heating cabinets.

JP-A-08145394 and JP-A-08145392 describe the use of plastics incorporating
10 anti-microbial compounds for use in ventilator apparatus.

EP-A-606762 describes a composition of a styrene polymer, an antibacterial agent and a compound having a specific functional group to produce an antibacterial resin composition.

US-A-4533435 describes an antimicrobial paper for packaging surgical supplies which
15 incorporates antibacterial compounds in a vinylic polymer binding agent.

The incorporation of antimicrobial agents is reviewed by D. Smock in *Plastics Formulating and Compounding*, March/April 1997 page 16 and *Plastics World* March 1992 page 58.

The present invention provides a plastics material which has biocidal activity which is useful in the manufacture of articles having biocidal properties e.g. for use in food storage
20 and preparation areas or medical applications. By "biocidal" we include biostatic activity, i.e. where the proliferation of microbiological species is reduced or eliminated in addition to true biocidal activity where microbiological species are killed. We also include activity against fungi, bacteria and other microbiological species in the meaning of "biocidal".

According to the invention, we provide a plastics material having biocidal activity
25 comprising an acrylic polymeric material and a biocidal compound wherein said acrylic material incorporates from 5% to 50% by weight of the total polymer present of a rubbery copolymer.

Preferred biocidal compounds include triclosan, compounds based on heavy metals, especially silver, on inorganic carriers such as zeolites, hydroxyapatite, zinc oxide, titanium dioxide, zirconium phosphate, isothiazolones, benzisothiazolin-3-one derivatives, 10, 10' oxybisphenoxyarsine, isothiazolines, zinc pyrithione, folpet (trichloromethyl thio-phthalimide). Examples of biocidal compounds which are effective in the invention include those sold under the trademarks DENSIL™ S (2,3,5,6 tetrachloro-4(methyl sulphonyl)pyridine available from Zeneca Ltd), SK-NOB-Z™ (a silver-containing zirconium phosphate available from Sanai of Japan) and VANQUISH™ (n-butyl 1,2-benzisothiazoline available from Zeneca Ltd). The present invention is directed towards improving the biocidal activity of acrylic materials containing known biocidal compounds and not to the biocidal compounds themselves and so it is envisaged that biocidal compounds other than those listed above may also be effectively used in the acrylic materials of the invention. The selection of any particular biocide for articles of the invention must be made with due regard to the end-use of the article and to the particular properties of the biocide, i.e. its activity against certain types of micro-organisms, toxicity, processability etc. It is not within the teaching of this document to provide guidance on the suitability of any one biocidal compound for any particular end-use.

The biocide is preferably present at a concentration of at least 0.25% by weight, more preferably at least 1% by weight of the polymer, e.g. 0.5 - 3% by weight.

The acrylic polymeric material comprises a homopolymer or copolymer of at least one C₁₋₆ alkyl (C₀₋₈ alk)acrylate. Preferred acrylic materials are homopolymers or copolymers of the methyl, ethyl, butyl, 2-ethylhexyl, cyclohexyl or phenyl esters of acrylic acid or methacrylic acid. One example of a preferred acrylic material comprises a homopolymer or copolymer of methyl methacrylate a copolymer comprising 80 - 100% of methyl methacrylate residues and 0 - 20% of a comonomer of a further acrylate or methacrylate selected from those materials listed above.

The composition of the acrylic material is selected according to the application in which the material is to be used. For example, if the plastics material is intended to be extruded into a sheet for subsequent thermoforming, e.g. to form a lining for a refrigerated cabinet, then an acrylic material formulated for thermal moulding should be selected. Such acrylic materials may advantageously be copolymers of methyl methacrylate with a minor

amount (e.g. 1 - 20 %wt) of an alkyl acrylate, e.g. methyl, ethyl or butyl acrylate and having a molecular weight of less than 500,000. For example a suitable copolymer is derived from about 90% methyl methacrylate and about 10% of ethyl acrylate having a weight average molecular weight of about 80,000 - 120,000. The acrylic plastics material
5 may be used as a coating over a base material which may be another polymer, such as another acrylic layer, PVC or a styrene based polymer for example. Acrylic materials have good weathering and chemical resistance as well as providing a high gloss finish and therefore a coating of acrylic having these properties may be provided to impart a suitable surface finish to another article. The acrylic polymer may contain additives such
10 as fillers, colorants, impact modifiers, matting agents etc.

The acrylic material incorporates from 5% to 50% by weight of the total polymer present of a rubbery copolymer. By a rubbery copolymer, we mean materials which have a glass transition temperature which is less than room temperature, preferably less than 0 °C, e.g. less than - 20 °C. We also include block copolymers which include a rubbery, low T_g block,
15 often with harder, higher T_g blocks. Such materials are well known for use as toughening agents for improving the impact resistance of acrylic materials. Suitable rubbery copolymers include copolymers of acrylates, methacrylates, styrene, acrylonitrile and/or olefins (especially butadiene). Examples of suitable materials include styrene - butadiene rubbers, such as the Cariflex™ polymers supplied by Shell, styrene - olefin copolymers
20 such as styrene ethylene-butylene styrene (optionally containing succinic anhydride) , styrene - ethylene propylene, e.g. the polymers sold under the Kraton trademark by Shell, methacrylate - butadiene - styrene (MBS) terpolymers, styrene - acrylonitrile copolymers, e.g. acrylonitrile - butadiene - styrene (ABS) terpolymers and core-shell type particles based on alkyl acrylates, e.g. butyl acrylate and styrene. Preferred types of rubbery
25 copolymer include copolymers of styrene, butadiene and a methacrylate compound, e.g. MBS copolymers. We have found that the incorporation of such rubbery materials enhances the biocidal effect of biocidal compounds incorporated into the acrylic materials. Preferably the plastics material comprises 15 - 50% by weight of rubbery polymer, especially 20 - 45%.

30 Suitable core-shell particles are discrete particles made by multi-stage graft copolymerisation normally by emulsion polymerisation techniques, each having a multi-layer structure and generally used to improve the impact resistance of polymers such as acrylic materials. A wide variety of these particles is available which differ in the

- type of copolymers from which they are made and the number and volume of shells present around the core. Typically the core is made from a methacrylate homo or copolymer and the first shell provides the rubbery material having a low T_g , typically made from an alkyl acrylate / styrene copolymer. This shell is often formulated to provide a
- 5 rubbery character for impact modification whilst being matched in refractive index to the acrylic substrate into which it is to be incorporated. A preferred type of copolymer to form the shell is based on n-butyl acrylate and an aromatic comonomer, e.g. styrene or a derivative thereof. A second or subsequent shell may also be present. Many suitable core-shell particles are commercially available, e.g. IR441 available from Mitsubishi Rayon
- 10 Co., and some commercially available grades of acrylic moulding materials include similar materials pre-compounded in to the polymer. One suitable core-shell particle is described in WO96/37531 and comprises a (meth)acrylic polymer core, a first shell comprising a low T_g polymer comprising 0 - 25% by weight of a styrenic monomer and 75 - 100% of an acrylic monomer, the (meth)acrylic monomer being capable of forming a
- 15 homopolymer having a T_g in the range -75 to -5 °C, the first shell representing at least 65% by volume of the combined volume of the core and first shell, and optionally a second shell which comprises a second (meth)acrylic polymer which may be the same as or different from the first (meth)acrylic polymer and the core and first shell together contain from 0.5 - 1.0 % by weight of a graft cross-linker.
- 20 The plastics material of the invention may have many applications. It is useful as a resin for moulding or extrusion applications, e.g. to make doors or panels for interior or exterior cladding applications etc. It may be provided in the form of a sheet material, e.g. for providing walls, linings etc or which may be suitable for forming into articles such as bathtubs e.g. by thermoforming. It may also be useful in the form of a curable resin, e.g.
- 25 a polymethyl methacrylate resin dissolved in methyl methacrylate and optionally containing a dispersion of fillers, colours and other functional particles for the manufacture of sinks, worktops, shower trays etc. The plastics material of the invention may be especially useful as a coating on a substrate. One benefit of this form of the invention is that a relatively small amount of the biocidally active plastic may be used to give biocidal
- 30 function to the surface of a non-biocidal substrate.

In a second aspect of the invention therefore, we provide a laminate material comprising a substrate material in contact with a layer of a plastics material having biocidal activity comprising an acrylic polymeric material and a biocidal compound wherein said acrylic

material incorporates from 5% to 50% by weight of the total polymer present of a rubbery copolymer. The thickness of the biocidal layer relative to the substrate may vary widely e.g. from 100% (i.e. equal thickness) to less than 1%. Normally the biocidal layer would be relatively thin, e.g. less than 50%, preferably less than 20% of the thickness of the substrate. One particular benefit of providing the plastics material having biocidal activity as a relatively thin layer on top of a transparent substrate, e.g.. transparent acrylic material, is that when the biocidal layer is sufficiently thin, a substantially transparent or translucent laminate material may be produced. This type of material is useful for producing articles in which a transparent or translucent effect is desired in combination with biocidal activity at the surface of the material. Such applications include material from which internal fittings for refrigerators are made, shelving for food products, shower screens etc.

The substrate material preferably comprises a thermoplastic material selected from the group comprising polystyrene and copolymers of styrene, acrylic polymers and copolymers, polyvinyl chloride and polyolefins and copolymers of these materials, e.g. acrylonitrile - styrene - butadiene (ABS). The substrate may contain additives such as fillers, pigments, plasticisers, impact modifiers, stabilisers etc. The biocidal layer may be applied to the substrate by coextrusion, extrusion coating, or adhesive or heat-and-pressure lamination of a sheet or film of the biocidal plastics material to the substrate material.

Of particular interest for the production of transparent materials is the use of core-shell impact modifier particles as the rubbery copolymer in the biocidal acrylic material or layer. This is because such core-shell particles may be formulated to have a refractive index which is matched to that of the acrylic material and therefore they may be incorporated into transparent grades of acrylic without reducing significantly the transparency of the acrylic material. Therefore it is possible to improve the biocidal effect of biocides incorporated into acrylic materials by incorporating a core-shell impact modifier which has been selected to match the refractive index of the acrylic material. When an acrylic material incorporating a core-shell particle and a biocide is provided as a thin (e.g. less than 200 μm) layer on a thicker transparent layer of acrylic material then the benefits of biocidal activity may be provided whilst retaining the transparency of the acrylic.

In a further aspect of the invention we provide a method of manufacturing a laminate material comprising the steps of extruding a plastics material having biocidal activity comprising an acrylic polymeric material and a biocidal compound wherein said acrylic material incorporates from 5% to 50% by weight of the total polymer present of a rubbery
5 copolymer on top of a layer of a substrate material. The substrate material preferably comprises a thermoplastic material which is coextruded with said plastics material having biocidal activity.

The invention will be further described with reference to the following examples.

Example 1 (Comparative)

10 An acrylic plaque was made by compounding together in a twin-screw extruder at 200 - 220 °C an injection moulding grade of acrylic polymer (Diakon™ LG156 from ICI Acrylics) with 2% of Vanquish™ 100 biocide from Zeneca Specialties. The biocide was added to the polymer melt by means of a liquid injection system and the resulting mixture was formed into a lace which was cut into small chips. A 50mm (2") x 75mm (3") x 3mm test
15 plaque was formed by injection moulding at 220 °C into a mould pre-heated to 40 °C. The sample plaque was then tested for fungal resistance and bacterial growth as described below. The results are given in Table 1.

Fungal Resistance

The samples were tested according to ASTM G21-90. Two 25mm squares were cut from
20 each sample and placed onto minimal salts agar plates. The plates were inoculated with a mixed fungal suspension containing aspergillus niger, aureobasidium pullulans, chaetomium globosum, gliocladium virens, penicillium funiculosum and then incubated for 28 days at 20°C. The samples were then examined for fungal growth and rated as follows: NG (no growth), TG (trace growth) <10% coverage on test piece, LG (light
25 growth) - 10 - 30% coverage, MG (moderate growth) 30 - 60% coverage, HG (heavy growth) 60% to complete coverage.

Bacterial growth Examples 1 - 10

0.2 ml of a 24 hour suspension of Escherichia coli was placed onto the surface of a test piece cut from a sample and then covered with a microscope coverslip. The samples
30 were incubated for 24 hours at 30°C and then rinsed with 10ml of sterile saline solution. The bacteria in the rinse water were then counted using a serial dilution counting method

in nutrient agar. The control sample was run with the E. coli suspension placed directly onto a sterile petri dish and covered with a coverslip.

Examples 2 - 5

Plaques of acrylic material were made and tested as described in Example 1, but with the addition of MBS (KANETM ACE 56, available from Kaneka) at varying levels at the compounding stage. The results are given in Table 1.

Examples 6 - 9

Sample plaques containing 35% by weight of MBS and varying levels of Vanquish 100 biocide were made and tested according to the method described above. The results are given in Table 1.

Example 10

A sample plaque containing 35% MBS and 2% DensilTM S biocide from Zeneca Specialties was made and tested by the method described above. The results are given in Table 1.

Table 1

Example	Wt% MBS	Wt% biocide	Bacterial count	Fungal growth rating
1	0	2.00	2.5×10^3	HG/HG
2	15	2.00	4.3×10^3	HG/HG
3	25	2.00	3.4×10^2	HG/HG
4	35	2.00	0×10^1	NG/NG
5	45	2.00	0×10^1	NG/NG
6	35	1.00	3.0×10^3	MG/MG
7	35	0.5	9.0×10^3	HG/HG
8	35	0.25	3.2×10^4	HG/HG
9	35	0.00	6.0×10^5	HG/HG
10	35	2.00	6.3×10^2	LG/MG

Example 11 Layered sample by coextrusion

A mixture containing 63 wt % DiakonTM LG156, 35% MBS polymer and 2% VanquishTM 100 antibacterial compound was compounded together and formed into polymer chips as described in Example 1. The resulting acrylic polymer was then coextruded at a thickness of 50 - 100 μm onto a 1 mm thick clear acrylic layer formed from unmodified DiakonTM

LG156. The sample appeared translucent. The bacterial growth tests were performed, as described below, on the side of the sample containing biocidal compound. The results are shown in Table 2. The ASTM G21-90 Fungal resistance test gave a result of "no growth".

5 Bacterial growth tests Examples 11 - 16

The samples were tested by a modified tile test vs Escherichia coli NCTC 8196. Sections of acrylic (50mm x 50mm) were wiped with isopropyl alcohol and then placed in petri dishes. The surface of the acrylic sample was inoculated with 0.1 ml of a culture of the organism in 1/4 strength Ringers solution. The acrylic was then covered with a sterilised
10 glass slide. The samples were maintained at 20 °C +/- 1 °C at > 90 % RH for 72 hours. The surviving organisms were recovered by washing / swabbing the acrylic and glass surfaces with 10 ml of Tryptone soya broth containing inactivators. Recoveries were performed at 24, 48 and 72 hours. The resulting broth was serially diluted and plate counts using plate count agar containing inactivators were performed. Plates were
15 incubated at 37 °C for 48 hours. Glass slides were used for control counts.

Example 12 (comparative)

A comparative sample containing 2% Vanquish and 98% LG156 was made as described in Example 11 and tested. The ASTM G21-90 Fungal resistance test gave a result of "moderate growth"

20 Example 13 (comparative)

A comparative sample was made by coextruding unmodified LG156 onto unmodified LG156 substrate as described in Example 11. The ASTM G21-90 Fungal resistance test gave a result of "moderate growth".

Example 14

25 A mixture containing 63 wt % Diakon™ LG156, 35% MBS polymer and 2% Irgasan™ DP300 (triclosan supplied by Ciba Speciality Chemicals) antibacterial compound was compounded together and formed into polymer chips and then coextruded and tested as described in Example 11.

Example 15 (comparative)

A sample containing 2% triclosan and 98% LG156 was made and tested. The results are shown in Table 2.

Example 16

A mixture containing 63 wt % Diakon™ LG156, 35% of a core-shell impact modifier based on MMA / butyl acrylate / styrene copolymers and made as described in the example of WO 96/37531, and 2% Vanquish™ 100 antibacterial compound was compounded together and formed into polymer chips and then coextruded and tested as described in Example 11. The coextruded sample was clear - transparent and very slightly yellow.

Table 2

Example	Rubber	Wt% rubber	Biocide	Wt% biocide	log ₁₀ E. coli count @ 20 °C			
					0 hours	24 hours	48 hours	72 hours
glass control		-	-	-	5.3	5.72	6.82	6.93
11	MBS	35	Vanquish	2	5.3	1.70	<1	<1
12 (comp)	-	-	Vanquish	2	5.3	5.28	5.40	4.95
13 (comp)	-	-	-	-	5.3	5.32	5.48	4.92
14	MBS	35	triclosan	2	5.3	4.49	2.54	1.90
15 (comp)	-	-	triclosan	2	5.3	4.30	4.18	4.30
16*	core-shell	35	Vanquish	2	6.38	4.77	3.91	1.9
17*	IR441 core-shell	35	Vanquish	2	6.38	4.85	2.92	<1

* samples 16 and 17 were tested at a different time using a bacterial sample having a different initial count.

Example 17

A mixture containing 63 wt % Diakon™ LG156, 35% of IR441™ which is a core-shell impact modifier (Mitsubishi Rayon Co), and 2% Vanquish™ 100 antibacterial compound was compounded together and formed into polymer chips and then coextruded and tested as described in Example 11. The coextruded sample was clear - transparent and very slightly yellow.

The samples were tested again for bacterial growth at 35 °C and the results are shown in Table 3.

Example 18

The biocide + acrylic + MBS compound made in Example 11 was re-compounded and then coextruded onto a clear acrylic substrate. The biocidal growth results were very similar to those of Example 11, showing that the material can withstand two extrusion operations, whilst maintaining its biocidal activity.

5

Table 3

Example	Rubber	Wt% rubber	Biocide	Wt% biocide	log ₁₀ E. coli count @ 35°C			
					0 hours	24 hours	48 hours	72 hours
glass control		-	-	-	6.00	7.48	7.70	8.00
11	MBS	35	Vanquish	2	6.00	1.00	-	-
12 (comp)	-	-	Vanquish	2	6.00	5.78	5.95	6.00
13 (comp)	-	-	-	-	6.00	4.90	5.00	5.48
14*	MBS	35	triclosan	2	5.30	1.00	-	-
15 (comp)*	-	-	triclosan	2	5.30	3.77	-	-
16	core-shell	35	Vanquish	2	6.00	3.78	3.95	2.48
17	IR441 core-shell	35	Vanquish	2	6.00	4.60	4.30	3.90

* samples 14 and 15 were tested at a different time using a bacterial sample having a different initial count.

Claims

1. A plastics material having biocidal activity comprising an acrylic polymeric material and a biocidal compound wherein said acrylic material incorporates from 5% to 50% by weight of the total polymer present of a rubbery copolymer.
- 5 2. A plastics material as claimed in claim 1, wherein said acrylic material incorporates from 25% to 50% by weight of the total polymer present of a rubbery copolymer.
3. A plastics material as claimed in either claim 1 or claim 2, wherein said biocidal compound is selected from the group comprising: triclosan, compounds based on heavy metals, especially silver, on inorganic carriers such as zeolites, hydroxyapatite, zinc oxide,
10 titanium dioxide, zirconium phosphate, isothiazolones, benzisothiazolin-3-one derivatives,
10, 10' oxybisphenoxyarsine, isothiazolines, zinc pyrithione, folpet (trichloromethyl thio-phthalimide), 2,3,5,6 tetrachloro-4(methyl sulphonyl)pyridine.
4. A plastics material as claimed in any of the preceding claims, wherein said biocidal compound comprises at least 0.25% by weight of the plastics material.
- 15 5. A plastics material as claimed in any preceding claim, which is in the form of a thermoformable sheet.
6. A plastics material as claimed in any preceding claim which is in the form of a surface coating layer supported on a substrate material.
7. A plastics material as claimed in any preceding claim which is in the form of a curable
20 resin composition.
8. A plastics material as claimed in any preceding claim which is in the form of a moulding resin or moulded article.
9. A plastics material as claimed in any preceding claim, wherein the rubbery material comprises a copolymers of an alkyl acrylate with styrene and optionally other
25 copolymers.

10. A plastics material as claimed in claim 9, wherein the rubbery material is in the form of a core-shell particle.
11. A laminate material comprising a substrate material in contact with a layer of a plastics material having biocidal activity comprising an acrylic polymeric material and a biocidal compound wherein said acrylic material incorporates from 5% to 50% by weight of the total polymer present of a rubbery copolymer.
12. A laminate material as claimed in claim 11, wherein said substrate material comprises a thermoplastic material selected from the group comprising polystyrene and copolymers of styrene, acrylic polymers and copolymers, polyvinyl chloride and polyolefins.
13. A method of manufacturing a laminate material comprising the steps of extruding a plastics material having biocidal activity comprising an acrylic polymeric material and a biocidal compound wherein said acrylic material incorporates from 5% to 50% by weight of the total polymer present of a rubbery copolymer on top of a layer of a substrate material.
14. A method as claimed in claim 13, wherein said substrate material comprises a thermoplastic material which is coextruded with said plastics material having biocidal activity.
15. A refrigerator part comprising a plastics material or a laminate material as claimed in any of claims 1 - 12.
16. A refrigerator part as claimed in claim 15, in the form of a lining, door panel, shelf or storage box.
17. A building component comprising a plastics material or a laminate material as claimed in any of claims 1 - 12.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 99/00686

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08K3/00 C08K5/00 C08L33/06 C08L51/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>DATABASE WPI Section Ch, Week 9504 Derwent Publications Ltd., London, GB; Class A12, AN 95-027690 XP002106525 & JP 06 313017 A (NIPPON GOSEI GOMU KK) , 8 November 1994 see abstract</p>	1,3,9
A	<p>EP 0 606 762 A (JAP. SYNTH. RUBBER) 20 July 1994 cited in the application see claims 1,6; examples</p>	1,3,9
A	<p>US 4 008 351 A (INOUE ET AL.) 15 February 1977 see examples 1,2</p>	1,6



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

18 June 1999

Date of mailing of the international search report

29/06/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Engel, S

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 99/00686

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 606762	A	20-07-1994	DE 69320167 D	10-09-1998
			DE 69320167 T	21-01-1999
			JP 6240094 A	30-08-1994
			US 5614568 A	25-03-1997
<hr/>				
US 4008351	A	15-02-1977	JP 1004166 C	30-06-1980
			JP 50146643 A	25-11-1975
			JP 53019345 B	20-06-1978
			AU 8125575 A	25-08-1977
			CA 1040098 A	10-10-1978
			DE 2521451 A	20-11-1975
			DK 216375 A	18-11-1975
			FR 2405804 A	11-05-1979
			FR 2301386 A	17-09-1976
			GB 1512243 A	24-05-1978
			GB 1518650 A	19-07-1978
			PH 11715 A	30-05-1978
			SE 7505659 A	18-11-1975
			SE 7903746 A	27-04-1979
<hr/>				